



(19)

(11) Publication number: **63155713 A**

Generated Document.

PATENT ABSTRACTS OF JAPAN

(21) Application number: **61301248**

(51) Intl. Cl.: **H01L 21/20 H01L 21/203 H01L 21/225**
H01S 3/18

(22) Application date: **19.12.86**

(30) Priority:
(43) Date of application publication: **28.06.88**
(84) Designated contracting states:

(71) Applicant: **HITACHI LTD**
(72) Inventor: **FUKUZAWA TADASHI**
(74) Representative:

(54) MANUFACTURE OF SEMICONDUCTOR FINE STRUCTURE

(57) Abstract:

PURPOSE: To easily manufacture many quantum fine structures by etching Si grown in a single quantum well structure in an arbitrary shape, further growing a semiconductor crystal, then heat treating it to diffuse Si, and partly deleting a semiconductor hetero boundary.

CONSTITUTION: A GaAs quantum well layer 3 is grown on the barrier layer 2 of a substrate 1. Then, an Si epitaxial layer 4 is grown. A wafer is fed to an etching chamber, an electron beam 6 is irradiated in an XeF2 gas, and Si- etched to obtain the remaining pattern 7 of the Si. It is again returned to the single crystal growing chamber, and a barrier layer 8 and a GaAs quantum well layer 9 are grown. Then, the Si is grown, an Si stripe 10 is formed, and a barrier layer 11 and a cap layer 12 are grown. Then, a heat treatment is conducted, and with an Si stripe 13 as a diffusion source the Si is diffused in the quantum well and the barrier layer. The mixed crystal 14 of the quantum well and the barrier layer is formed at a hetero boundary in which the Si is diffused. A buried hetero structure is obtained in a region 15 in which the Si is not diffused.

COPYRIGHT: (C)1988,JPO&Japio

